Marine Paint Manual

Reference No.: 03-01CN

Issue Date: June 2020

NIPPON A-MARINE FINISH H

A high solid acrylic based finish with good weathering resistance and workability. It satisfies regulation value in the "Limit of harmful substances of marine coatings" (GB 38469 2019) issued by People's Republic of China.

Suitable Use Finish for boottop, topsides, decks, superstructures, etc.

Type Acrylic

White, Black, 445 Red Oxide, Gray*, Cream*, Blue*, Green*,

Color Other colors (see Note 3)

Gloss Semi-gloss

Volume Solids $50 \pm 2\%$ (ISO3233:1998)

Typical Dry Film Thickness $30 \sim 50 \ \mu m$ Approx. Wet Film Thickness $60 \sim 100 \ \mu m$

Theoretical Coverage 14.29 m²/ L (35 µm)

Drying Time Surface Dry 40 minutes (5°C) 20 minutes (20°C) 15 minutes (30°C)

Dry Hard 2 hours $(5^{\circ}C)$ 1 hour $(20^{\circ}C)$ 30 minutes $(30^{\circ}C)$

Interval before Overcoating Min. 6 hours (5°C) 3 hours (20°C) 2 hours (30°C) (by self) Max. - (5°C) - (20°C) - (30°C)

VOC Values 470 g / L as supplied

Cleaning Thinner NIPPON MARINE THINNER 200

Thinning is not normally required. Consult the local representative for

advice during application in extreme conditions.

Application Method Airless Spray Tip range 0.43 ~ 0.48 mm

Fan angle $55 \sim 69^{\circ}$

Output pressure 100 ~ 150 kg / cm²

Brush For touching up small areas only

Package 20L

Japan Local Brand NIPPON A-MARINE FINISH H

Flash Point 31 °C (ISO3679:2015)

Surface Preparation All surfaces to be coated should be clean, dry and free from

contamination.

High pressure fresh water wash and remove all oil / grease,

soluble contaminants and other foreign matters.

Safety Take precautions to avoid skin and eye contact (i.e. gloves,

goggles, face masks, barrier creams etc.)

Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor

concentrations within safe limits.

Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.



Marine Paint Manual

PPON A-MARINE FINISH H Issue Date: June 2020 (CN)

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Chlorinated rubber paints should not be applied on top of A-marine finish.
- 3) The following colours are available as our standard.

Gray: 070, 065, 060, 055, 050, 040 Cream: 332, 335

Blue: 606, 808, 837 Green: 442, 505, 535, 225

- 4) VOC values may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.
- 5) NIPPON A-MARINE FINISH H is supplied only in China.
- 6) Store the paints in paint store.