

Marine Paint Manual

Reference No. 05 - 01
Issue Date: July 2019 (ES)

UNIPRIME 100

UNIPRIME 100, is an abrasion resistant epoxy anticorrosive. With excellent resistance to water/seawater, it can be used for not only outer hull but also above water areas. This multipurpose anticorrosive primer enables unlimited intervals for by-self coating, and for various kinds of finishes in above water areas.

Suitable Use	Anticorrosive for outer hull (including bottom, boottop and topsides), decks, superstructure, cargo holds, etc.						
Type	Epoxy (High build / Two-pack)						
Color	Gray, Red Oxide						
Gloss	Flat						
Volume Solids	63 ± 2% (ISO3233:1998)						
Typical Dry Film Thickness	100 ~ 250 μm						
Approx. Wet Film Thickness	159 ~ 397 μm						
Theoretical Coverage	5.04 m²/L (125 μm)						
Drying Time	Surface Dry	2 hours (5°C)	1 hour (20°C)	1 hour (30°C)			
	Dry Hard	24 hours (5°C)	10 hours (20°C)	8 hours (30°C)			
	(for LT HARDENER)						
	Surface Dry	2 hours (5°C)	2 hours (10°C)	1 hour (20°C)			
	Dry Hard	20 hours (5°C)	16 hours (10°C)	8 hours (20°C)			
Interval before Overcoating (by self)	Min.	24 hours (5°C)	10 hours (20°C)	8 hours (30°C)			
	Max.	— (5°C)	— (20°C)	— (30°C)			
	* As long as no one steps in the painted area, the interval can be shortened to at minimum 4 hours (20°C).						
	(for LT HARDENER)						
	Min.	20 hours (5°C)	16 hours (10°C)	8 hours (20°C)			
	Max.	— (5°C)	— (10°C)	— (20°C)			
	* As long as no one steps in the painted area, the interval can be shortened to at minimum 4 hours (10°C).						
	Thinner	NIPPON MARINE THINNER 600					
	Application Method	Airless Spray	Tip range	0.53 ~ 0.64 mm			
Fan angle			45° ~ 60°				
(T/U)			30°				
Output pressure			150 ~ 250 kg/cm²				
	Brush / Roller	For touching up small areas only					
	BASE 3.85 / HARDENER 1						
Mixing Ratio by Volume							

Marine Paint Manual

UNIPRIME 100

Issue Date: July 2019 (ES)

Pot Life After Mixing	7 hours (5°C) 5 hours (20°C) 4 hours (30°C) (for LT HARDENER) 3 hours (5°C) 2 hours (10°C) 1 hour (20°C)
Packaging	Two Packs
Japan Local Brand	UNIPRIME 100
Flash Point	BASE 14°C, HARDENER 30°C, LT HARDENER 30°C
Surface Preparation	Blast cleaned to ISO-Sa 2 ¹ / ₂ or power tool cleaned to St 3 is recommended.
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.) Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits. Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Prior to overcoating, remove heavily chalked layer, salt contamination, etc. by fresh water washing.
- 3) Two types of the hardener are available for Summer version and Winter version.
- 4) For availability of product consult Nippon Paint Marine representatives.
- 5) Unit size and filled volumes can vary due to local regulations.
- 6) Store the paints in paint store.