

Marine Paint Manual

Reference No. : 06 - 03

Issue Date: July 2019 (ES)

ICEBAN 1600

A super high solids, low VOC, two pack pure epoxy abrasion and low frictional resistant anticorrosive for underwater hull of ice-going vessels. Super high build coating with a single coat is available. It facilitates the sailing in ice bound areas, by protecting outer hull from corrosion and keeping the surface smooth to reduce frictional resistance to ice.

Suitable Use	Underwater hull of ice-going vessels (Ice coating)				
Type	Pure epoxy (High solids / Abrasion and low frictional resistant / Two-pack)				
Color	Red Oxide, Black				
Gloss	Gloss				
Volume Solids	95 ± 2% (ISO3233:1998)				
Typical Dry Film Thickness	500 μm				
Approx. Wet Film Thickness	526 μm				
Theoretical Coverage	1.90 m²/ L (500 μm)				
Drying Time	Surface Dry	24 hours (10℃)	16 hours (15℃)	5 hours (25℃)	
	Dry Hard	4 days (10℃)	78 hours (15℃)	48 hours (25℃)	
Interval before Overcoating (by self)	Min.	8 hours (10℃)	6 hours (15℃)	3 hours (25℃)	
	Max.	16 hours (10℃)	12 hours (15℃)	6 hours (25℃)	
Thinner	Dilution Not Allowed. For cleaning, use NIPPON MARINE THINNER 600.				
Application Method	Airless Spray	Dedicated Painting Equipment (Hot Twin Feed) See “Painting Procedure” for the details.			
		Brush For touching up small areas only			
Mixing Ratio by Volume	BASE 2 / HARDENER 1				
Pot Life after Mixing	5 minutes (45℃)				
Packaging	Two Packs				
Japan Local Brand	ICEBAN 1600				
Flash Point	BASE 30 °C, HARDENER 38 °C				
Surface Preparation	Blast cleaned to ISO-Sa 2 ¹ / ₂ is recommended.				
	All surfaces to be coated should be clean, dry and free from contamination.				
	High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.				

Marine Paint Manual

ICEBAN 1600

Issue Date: July 2019 (ES)

Safety

Take precautions to avoid skin and eye contact (i.e. air-line masks and protective equipment etc.)
Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.
Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Do not dilute this product for the application. For cleaning, use NIPPON MARINE THINNER 600.
- 3) For availability of product consult Nippon Paint Marine representatives.
- 4) Unit size and filled volumes can vary due to local regulations.
- 5) Store the paints in paint store.