

Marine Paint Manual

Reference No. : 13 - 05

Issue Date: July 2019 (ES)

ECOSILK

A unique and ultimate biocide-free antifouling paint based on the same technology of the silicone elastomer. Low frictional resistance to prevent shipfouling organisms from settling is realized by the silicone elastomer that has super water repelling property. ECOSILK differs from the other A/F paints in that it contains no biocide taking the environmental issues into consideration. It is designed especially for high speed and high activity ships. Its characteristics, that it is not of a polishing type with less film deterioration and not chemically altered, ensure the stable and long term antifouling performance to prolong the intervals of docking.

Suitable Use	Finish for super water repellent antifouling for high speed / high activity ships					
Type	Silicone Elastomer					
Color	Gray					
Gloss	Gloss					
Volume Solids	72 ± 2% (ISO3233:1998)					
Typical Dry Film Thickness	150 μm					
Approx. Wet Film Thickness	208 μm					
Theoretical Coverage	4.80 m²/ L (150 μm)					
Drying Time	Surface Dry	10 hours	(5°C)	4½ hours	(20°C)	2 hours (30°C)
	Dry Hard	13 hours	(5°C)	6½ hours	(20°C)	3½ hours (30°C)
Interval before Overcoating (by self)	Min.	15 hours	(5°C)	7 hours	(20°C)	4½ hours (30°C)
	Max.	—	(5°C)	—	(20°C)	— (30°C)
Interval before Immersion	24 hours or more					
Thinner	Dilution Not Allowed. For cleaning, use NIPPON MARINE THINNER 600.					
Application Method	Airless Spray	Tip range	0.53 mm			
		Fan angle	55 ~ 69°			
		Output pressure	above 150 kg / cm²			
Mixing Ratio by Volume	Brush / Roller	For touching up small areas only				
	BASE 15 / CURING AGENT 4 / ADDITIVE 1					
Pot Life after Mixing	3 hours (5°C)	1⅓ hours (20°C)	45 minutes (30°C)			
Packaging	Three Packs					
Japan Local Brand	ECOLOSILK					
Flash Point	BASE 25 °C, CURING AGENT 25 °C, ADDITIVE 35 °C					
Surface Preparation	All surfaces to be coated should be clean, dry and free from contamination.					
	High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.					

Marine Paint Manual

ECOLOSilk

Issue Date: July 2019 (ES)

Safety

Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)
Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.
Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Prior to use, refer to painting procedure.
- 3) For availability of product consult Nippon Paint Marine representatives.
- 4) Unit size and filled volumes can vary due to local regulations.
- 5) Store the paints in paint store.