

Marine Paint Manual

Reference No. : 17 - 08

Issue Date: June 2020 (ES)

NEOGUARD 100

A flexible, surface tolerant multipurpose epoxy paint designed for maintenance and repair/upgrading of topsides, exposed decks, exterior of superstructure, cargo holds, etc. It provides both properties of anticorrosive and finish. Applicable to hand tool-cleaned surfaces as well as directly over existing coatings. Ships in service can be upgraded by the long-term maintenance-free system. It offers excellent resistance to water and corrosion, and can be applied directly over existing acrylic, chlorinated rubber and alkyd resin coatings.

Suitable Use	Anticorrosive for topsides, exposed decks, outfittings on decks, hatch covers, exterior for superstructures, cargo holds, engine room and pump room, void spaces, cofferdams, etc.						
Type	Epoxy (High build / Surface tolerant / Two-pack)						
Color	White, Black, Red Oxide, Gray (070, 060, 040), Green (442, 505)						
Gloss	Semi-gloss						
Volume Solids	61 ± 2% (ISO3233:1998)						
Typical Dry Film Thickness	100 ~ 200 μm						
Approx. Wet Film Thickness	164 ~ 328 μm						
Theoretical Coverage	6.10 m ² / L (100 μm)						
Drying Time	Surface Dry	2 hours	(5℃)	1 hour	(20℃)	40 minutes	(30℃)
	Dry Hard	24 hours	(5℃)	12 hours	(20℃)	6 hours	(30℃)
	Full Cure	14 days	(5℃)	7 days	(20℃)	5 days	(30℃)
Interval before Overcoating (by self)	Min.	24 hours	(5℃)	12 hours	(20℃)	6 hours	(30℃)
	Max.	—	(5℃)	—	(20℃)	—	(30℃)
Thinner	NIPPON MARINE THINNER 600 (0 ~ 10%, by volume)						
Application Method	Airless Spray	Tip range	0.48 ~ 0.59 mm				
		Fan angle	55 ~ 62°				
		(T/U)	30°				
		Output pressure	150~200 kg / cm ²				
Mixing Ratio by Volume	Brush / Roller	For touching up small areas only					
	BASE 3.8 / HARDENER 1						
	Pot Life after Mixing	5 hours (5℃)	3 hours (20℃)	2 hours (30℃)			
Packaging	Two Packs						
Japan Local Brand	NEOGUARD 100						
Flash Point	BASE 14 °C, HARDENER 6 °C						
Surface Preparation	Blast cleaned to ISO-Sa 2 or Power tool cleaned to ISO-St 2 is recommended.						
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.) Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits. Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.						

Marine Paint Manual

NEOGUARD 100

Issue Date: June 2020 (ES)

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Water soluble rust and salt tend to remain in pitted areas where heavy and/or thick rust has been removed. Clean such areas with high-pressure fresh water.
- 3) Prior to full coat of NEOGUARD 100, treat heavily corroded areas in accordance with Note 2), then apply NEOGUARD BULCON.
- 4) For a higher level of anticorrosive performance and more aesthetic appearance, apply epoxy or urethane resin based paints as finishes. For further details, please contact Nippon Paint Marine Coatings.
- 5) For availability of product consult Nippon Paint Marine representatives.
- 6) Unit size and filled volumes can vary due to local regulations.
- 7) Store the paints in paint store.