

Marine Paint Manual

Reference No. : E 10/16

Issue Date: July 2018 (EU)

EVER COOL FINISH (E)

A high heat-shield paint based on polyurethane resin with excellent weathering resistance and gloss retention. As it contains special pigment with low endothermic property under the infrared ray region, it can restrain rise in surface temperature of paint film through high heat-shield.

Suitable Use	Finish for superstructures, hatch covers, compass deck, other exposed weather decks, etc.						
Type	Polyurethane (Two-pack)						
Color	(Product Code)*	White, Grey N-6.0, Grey N-4.0 (RAL 7024), etc. (FAEBE)*					
	HARDENER	(FAX 1541)*					*Not color code (See note 5)
Gloss	Gloss						
Volume Solids	46 ± 2% (ISO3233:1998) depending on colour shade						
Typical Dry Film Thickness	40 μm						
Approx. Wet Film Thickness	90 μm						
Theoretical Coverage	11.50 m ² / L (40 μm)						
Drying Time	Surface Dry	4 hours	(5°C)	2 hours	(20°C)	1 hours	(30°C)
	Dry Hard	20 hours	(5°C)	12 hours	(20°C)	8 hours	(30°C)
	Full Cure	14 days	(5°C)	7 days	(20°C)	5 days	(30°C)
Interval before Overcoating (by self)	Min.	20 hours	(5°C)	12 hours	(20°C)	8 hours	(30°C)
	Max.	–	(5°C)	–	(20°C)	–	(30°C)
Thinner (Code. No.)	NIPPON MARINE THINNER 700 (VFE 35) / 5 ~ 15%, by volume						
Application Method	Airless Spray	Tip range	0.38 ~ 0.48 mm (0.015" - 0.019")				
		Fan angle	55° ~ 60°				
		Output pressure	120 ~ 150 kg / cm ²				
	Brush / Roller	For touching up small areas only					
Mixing Ratio by Volume	BASE 5 / HARDENER 1						
Pot Life after Mixing	8 hours (5°C) 6 hours (20 °C) 4 hours (30°C)						
Typical Package	20L (BASE 16.7 L, HARDENER 3.3 L)						
Flash Point	25°C						
Surface Preparation	All surfaces to be coated should be clean, dry and free from contamination.						
	High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.						
Generals	For commercial use only. Attention - Avoid exposure - obtain special instructions before use.						

Marine Paint Manual

EVER COOL FINISH (E)

Issue Date: July 2018 (EU)

Safety

Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)
Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.
Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) During applications at high temperatures, use NIPPON MARINE THINNER 750.
- 3) Store the paints in paint store.
- 4) The following colours are available as our standard. (on request)
- 5) This code is internal product code of Nippon Paint Marine Europe. Please be careful as it isn't color code.
- 6) Use the dedicated EVER COOL primer for ships in service when in maintenance and repair.