

## Marine Paint Manual

Reference No. : E 10/16

Issue Date: March 2019 (EU)

### NIPPON A-MARINE FINISH 100

An acrylic based finish with good weathering resistance, high gloss, and workability.

Suitable Use	Finish for boottop, topsides, decks, superstructures, etc.						
Type	Acrylic						
Color	(Product Code)*	White	(PAS 9010)*	Black	(PAS 9005)*		
		Gray	(PAS 7001)*	Other colors (see Note No.3)			
		*Not color code (See note 5)					
Gloss	Gloss						
Volume Solids	48 ± 2% (ISO3233:1998)						
Typical Dry Film Thickness	40 μm						
Approx. Wet Film Thickness	85 μm						
Theoretical Coverage	11.76 m²/ L (40 μm)						
Drying Time	Surface Dry	4 hours	(5°C)	1 hours	(20°C)	50 minutes	(30°C)
	Dry Hard	12 hours	(5°C)	6 hours	(20°C)	5 hours	(30°C)
Interval before Overcoating ( by self )	Min.	12 hours	(5°C)	6 hours	(20°C)	5 hours	(30°C)
	Max.	—	(5°C)	—	(20°C)	—	(30°C)
Thinner (Code. No.)	NIPPON MARINE THINNER 200 (VCC 20M) / 0 ~ 5%, by volume						
Application Method	Airless Spray	Tip range	0.43 ~ 0.48 mm (0.017" - 0.019")				
		Fan angle	55 ~ 69°				
		Output pressure	100 ~ 150 kg / cm²				
	Brush	For touching up small areas only					
Package	20L						
Flash Point	25 °C						
Surface Preparation	All surfaces to be coated should be clean, dry and free from contamination.						
	High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.						
Generals	For commercial use only. Attention - Avoid exposure - obtain special instructions before use.						
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)						
	Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.						
	Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.						

---

## ***Marine Paint Manual***

NIPPON A-MARINE FINISH 100

Issue Date: March 2019 (EU)

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Chlorinated rubber paints should not be applied on top of A-marine finish 100.
- 3) The following colours are available as our standard. (on request)
- 4) Store the paints in paint store.
- 5) This code is internal product code of NPMEU. Please be careful as it isn't color code.