Marine Paint Manual

Reference No.: E 10/16

Issue Date: September 2018 (EU)

NIPPON A-MARINE FINISH (E)

An acrylic based finish with good weathering resistance and workability. To be applied on primers of similar composition or on modified epoxy coats. Suitable for use abovedeep load-line on ship's hull and all exterior areas.

Suitable Use Finish for boottop, topsides, decks, superstructures, etc.

Type Acrylic

Color (Product Code)* White (CSE 9010)* Black (CSE 9005)*

Gray (CSE 7001)* Other colors (see Note No.3)

*Not color code (See note 5)

Gloss Gloss

Volume Solids $42 \pm 2\%$ (ISO3233:1998)

Typical Dry Film Thickness 40 μm Approx. Wet Film Thickness 95 μm

Theoretical Coverage 10.50 m²/ L (40 µm)

Drying Time Surface Dry 4 hours (5°C) 1 hours (20°C) 50 minutes (30°C)

Dry Hard 12 hours $(5^{\circ}C)$ 6 hours $(20^{\circ}C)$ 5 hours $(30^{\circ}C)$

Interval before Overcoating Min. 12 hours $(5^{\circ}C)$ 6 hours $(20^{\circ}C)$ 5 hours $(30^{\circ}C)$ (by self) Max. - $(5^{\circ}C)$ - $(20^{\circ}C)$ - $(30^{\circ}C)$

Thinner (Code. No.) NIPPON MARINE THINNER 200 (VCC 20M) / 0 ~ 5%, by volume

Application Method Airless Spray Tip range $0.43 \sim 0.48 \text{ mm } (0.017" - 0.019")$

Fan angle $55 \sim 69^{\circ}$

Output pressure 100 ~ 150 kg / cm²

Brush For touching up small areas only

Package 20L Flash Point 25 °C

Surface Preparation All surfaces to be coated should be clean, dry and free from

contamination.

High pressure fresh water wash and remove all oil / grease,

soluble contaminants and other foreign matters.

Generals For commercial use only. Attention - Avoid exposure - obtain special

instructions before use.

Safety Take precautions to avoid skin and eye contact (i.e. gloves,

goggles, face masks, barrier creams etc.)

Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor

concentrations within safe limits.

Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

Marine Paint Manual

NIPPON A-MARINE FINISH (E)

Issue Date: September 2018 (EU)

< Note >

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Chlorinated rubber paints should not be applied on top of A-marine finish (E).
- 3) The following colours are available as our standard. (on request)
- 4) Store the paints in paint store.
- 5) This code is internal product code of NPMEU. Please be careful as it isn't color code.