

Marine Paint Manual

Reference No. : E 10/16

Issue Date: February 2019 (EU)

TETZSOL 200 SILVER M (E)

A highly heatresistant and oilresistant finish containing alkyd resin as a binder. It can withstand at high temperatures up to 150°C.

Suitable Use	Heat-resistant finish for boilers, engines, etc.						
Type	Alkyd (up to 150°C)						
Color (Product Code)*	Silver	(SEE 9006)*	*Not color code (See note 4)				
Gloss	Gloss						
Volume Solids	42 ± 2 % (ISO3233:1998)						
Typical Dry Film Thickness	25 μm						
Approx. Wet Film Thickness	60 μm						
Theoretical Coverage	16.80 m ² / L (25 μm)						
Drying Time	Surface Dry	6 hours	(5°C)	3 hour	(20°C)	2 hours	(30°C)
	Dry Hard	24 hours	(5°C)	12 hours	(20°C)	8 hours	(30°C)
Interval before Overcoating (by self)	Min.	24 hours	(5°C)	12 hours	(20°C)	8 hours	(30°C)
	Max.	—	(5°C)	—	(20°C)	—	(30°C)
Thinner (Code. No.)	NIPPON MARINE THINNER 100 (VSK 23) / 0 ~ 5%, by volume						
Application Method	Airless Spray	Tip range	0.38 - 0.48 mm (0.015" - 0.019")				
		Fan angle	55 ~ 69°				
		Output pressure	120 ~ 150 kg / cm ²				
	Brush / Roller	For touching up small areas only					
Package	20L						
Flash Point	27°C						
Surface Preparation	All surfaces to be coated should be clean, dry and free from contamination.						
	High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.						
Generals	For commercial use only. Attention - Avoid exposure - obtain special instructions before use.						
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)						
	Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.						
	Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.						

Marine Paint Manual

TETZSOL 200 SILVER M (E)
Issue Date: February 2019 (EU)

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Detachment may occur if the coating is heated and dried at a rapidly rising temperature due to machinery operation. To prevent this, slowly increase the temperature by no more than 10°C per minute or run the machinery intermittently.
- 3) Store the paints in paint store.
- 4) This code is internal product code of NPMEU. Please be careful as it isn't color code.