Marine Paint Manual

Reference No. :E 10/16 Issue Date: December 2018 (EU)

UNIPRIME 30 (E)

A high performance one-pack anticorrosive with good resistance to water, seawater and alkaline. It has tie-coat property and superior hold-up property which enables high film build. It shows excellent adhesiveness to various A/F paints and NIPPON A-MARINE FINISH. With regard to incorporating aluminium type, it can be applied for ship's hull on bare steel surfaces, shop-primers, or existing paints. Also can be used as sealer coat.

	Suitable Use		Anticorrosive for hull								
Туре		Special synthetic resin (The colour of Silver / Reddish Silver is included aluminium paste.)									
Color	(Product Code)*	Silver (CRGD 9206)*				Reddish Silver		(CRGD 9406)*			
		Redbrown (CRGD 3500)*					Brown		(CRGD 8700)*		
		Buff	(CRGD	1501)*			Black		(CRGD 9005	5)*	
							*Not color code (See note 3)				
Gloss		Flat									
(for incorporating aluminium, Silver and Reddish Silver)											
Volume Solids		46 ± 2% (ISO3233:1998)									
Typical Dry Film Thickness		70 μm									
Approx. Wet Film Thickness		152 μm									
Theoretical Coverage		6.57 m²/ L (70 μm)									
(except for Silver and Reddish Silver)											
Volume Solids		40 ± 2% (ISO3233:1998)									
Typical Dry Film Thickness		70 μm									
Approx. Wet Film Thickness		175 µm									
Theoretical Coverage		5.70 m²/ L (70 μm)									
Drying Time		Surface D)ry [·]	1 hour	(5°C)	30	minutes	(20°C)	20 minutes	; (30°C)	
, ,			-		• •			. ,	3 hours	. ,	
Interval	before Overcoating	Min.	-	7 hours	(5°C)	4	hours	(20°C)	3 hours	(30°C)	
(by sel	f)	Max.			(5°C)			(20°C)	—	(30°C)	
Thinne	r (Code. No.)	NIPPON MARINE THINNER 200 (VCC 20M) / 0 ~ 5%, by volume									
Application Method		Airless Sp	Tip range 0.48 ~ 0.53 mm (0.019" - 0.021")								
		Fan angle					55 ~ 69°				
		Output pressure 100 ~ 150 kg / cm²									
		Brush For touching up small areas only									
Packag	le	20L									
Ŭ	·	Package	may var	y from	country	to o	country.				
Japan I	_ocal Brand	UNIPRIME A/C									
Flash F		24 °C									
	e Preparation	Blast cleaned to ISO-Sa $2^{1}/_{2}$ or power tool cleaned to St 3									
		is recommended.									
Genera	lls	For commercial use only. Attention - Avoid exposure - obtain special									
			instructions before use.								

Marine Paint Manual

UNIPRIME 30 (E) Issue Date: December 2018 (EU)

SafetyTake precautions to avoid skin and eye contact (i.e. gloves,
goggles, face masks, barrier creams etc.)Proper ventilation and protective measures must be provided
during applications and drying period to keep solvent vapor
concentrations within safe limits.Prior to use, obtain, consult and follow the SDS for this
product concerning health and safety information.

<<u>Note</u>>

1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

2) Store the paints in paint store.

3) This code is internal product code of NPMEU. Please be careful as it isn't color code.