

The Crew Series


ONBOARD MAINTENANCE



High build Polyurethane Finish for Superstructures

NIPPON U-MARINE CREW


White




Acrylic Finish for Exterior

NIPPON A-MARINE CREW


White




Red Oxide



060 Gray




225 Green



Alkyd Finish for Interior

NIPPON O-MARINE CREW


White




Red Oxide



060 Gray




225 Green




Multi purpose Pure Epoxy Primer/Finish for Corrosion Protection

NIPPON E-MARINE CREW


White




Red Oxide



060 Gray



225 Green



※Colours shown just for the purpose of reference

The CREW Series

OBM paints of the crew, by the crew, for the crew



The Crew series offers a simplified range of essential paints for Onboard Maintenance, which is specially designed for easy management and application by the crew.

The Crew series rundown



Optimized maintenance by the crew



Easy application with brush and roller



Onboard maintenance friendly



Colours in high demand



Valuable Ranges

The
CREW
Series



Description


Product name	Feature	Suitable use	Colour	Gloss	Volume Solids	Typical DFT	Theoretical Coverage	Drying Time(20°C)	Cleaner ※
NIPPON U-MARINE CREW	A two-packed high build polyurethane finish paint with excellent weathering resistance and gloss retention	Topcoat for superstructures	White	Gloss	52±2% (ISO3233:1998)	25 ~ 50 µm	13 m ² / L (30µm)	Surface Dry : 40 minutes Dry Hard : 10 hours	Nippon Marine Thinner 700
NIPPON A-MARINE CREW	An acrylic based finish paint with good weathering resistance and workability for exposed areas like decks and superstructures	Top coat for decks, hatch coaming, hatch covers, superstructures	White / Red Oxide / 060 Gray / 225 Green	Semi-gloss	43±2% (ISO3233:1998)	30 ~ 50 µm	10.75 m ² / L (40µm)	Surface Dry : 20 minutes Dry Hard : 1 hour	Nippon Marine Thinner 200
NIPPON O-MARINE CREW	An ideal alkyd finish paint for interior, ceiling, wall and floor designed for easy application	Top coat for ceiling & wall of accommodation, engine room, stores etc.	White / Red Oxide / 060 Gray / 225 Green	Gloss	57±2% (ISO3233:1998)	30 ~ 40 µm	14.25 m ² / L (40µm)	Surface Dry : 30 minutes Dry Hard : 7 hours	Nippon Marine Thinner 100
NIPPON E-MARINE CREW	A multipurpose epoxy paint provided both anti-corrosion properties and finish	Decks, holds, engine room, stores	White / Red Oxide / 060 Gray / 225 Green	Matt	61±2% (ISO3233:1998)	75 ~ 100 µm	8.13 m ² / L (75µm)	Surface Dry : 2.5 hours Dry Hard : 4 hours	Nippon Marine Thinner 600

※No thinning is recommended

Crew Supply Location

Associates	Japan		Korea	China	Taiwan	HK	Singapore
Supply Location ※Country and main port	Japan	UAE	Korea	China	Taiwan	Hong Kong	Singapore
	• Tomakomai • Onahama • Kashima • Tokyo • Kawasaki • Yokohama • Chiba • Shimizu • Nagoya • Toyohashi • Kobe • Osaka • Fukuyama • Mizushima • Sakaide • Tobata	• Fujairah • Khor Fakkan	• Busan • Ulsan • Masan • Jinhae • Kwangyang • Yeosu • Pohang • Samcheonpo • Mokpo • Kunsan • Pyongtaek	• Shanghai • Lianyungang • Nantong • Taicang • Zhenjiang • Rizhao • Qingdao • Caofeidian • Tianjin • Xiamen	• Kaohsiung • Taichung • Mailio • Keelung • Taipei • Suao • Hualien	• Hong Kong • South China • Guangxi • Shekou • Guangzhou	• Singapore • Malaysia • Philippines • Subic • Cebu • Thailand • Laemchabang • Indonesia • Jakarta • Batam • Vietnam • Haiphong

NPM Network



● Head Quarters

● Associates

GERMANY, TURKEY, KOREA, CHINA, TAIWAN, HONGKONG, MALAYSIA, SINGAPORE, U.S.A

● Business Partner

● Production / Warehouses / Technical Service