

Marine Paint Manual

Reference No. : 16 - 05 (E)

Issue Date: November 2021 (EU)

NEOGUARD BULCON (E)

A super high-build, durable surface tolerant pure epoxy anticorrosive which has excellent substrate wettability and can be applied to hand tool-cleaned surfaces as well as directly over exiting coatings for maintenance and repair. It can be applied virtually anywhere, and even a single coat is effective in areas where heavy corrosion is anticipated or in places already rusted or pitted, providing high performance of rust protection.

Suitable Use	Filler for exposed areas, immersed area, internal areas and other ship areas, e.g. welding lines, edges, etc.		
Type	Pure epoxy (Super high build / Surface tolerant / Two-pack)		
Color (Product Code)*	Gray (ERLQ 7501)*	Olivegreen (ERLQ 6500)*	
	Hardener (ERQX 9105 for Gray and Olivegreen)*		

*Not color code (See note 7)

Gloss	Flat			
Volume Solids	90 ± 2% (ISO3233:1998)			
Typical Dry Film Thickness	1.0 ~ 2.0 mm			
Approx. Wet Film Thickness	1.1 ~ 2.2 mm			
Theoretical Coverage	0.90 m ² /kg(1 mm)			
Drying Time	Surface Dry	4 hours (5°C)	2 hours (20°C)	1 hour (30°C)
	Dry Hard	48 hours (5°C)	16 hours (20°C)	8 hours (30°C)
	Full Cure	14 days (5°C)	7 days (20°C)	5 days (30°C)
Interval before Overcoating (by self)	Min.	48 hours (5°C)	24 hours (20°C)	16 hours (30°C)
	Max.	7 days (5°C)	5 days (20°C)	3 days (30°C)
Thinner	NIPPON MARINE THINNER 600 (for equipment cleaning only).			
Application Method	Brush / Spatula			
Mixing Ratio by Weight	BASE 1.5 / HARDENER 1			
Pot Life after Mixing	1.5 hours (5°C), 1 hour (20°C), 30 minutes (30°C)			
Typical Package	7.5 kg (BASE 5 kg, HARDENER 2.5 kg)			
Flash Point	BASE 24°C, HARDENER 39°C			

Surface Preparation	Remove grease, oil contamination with thinner or cleaning agents. Remove thick rust and existing old paint by chipping or wire brushing to St 2. Best results will be achieved by grit blasting Sa 2. Wet surface have to be wiped dry.
---------------------	--

Generals	For commercial use only. Attention - Avoid exposure - obtain special instructions before use.
----------	---

Marine Paint Manual

NEOGUARD BULCON (E)

Issue Date: November 2021 (EU)

Safety

Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)
Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.
Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Thoroughly mix Base and Hardener in specified amount with a mixing stick, a mixing knife, a spatula, etc.
- 3) In order to secure the film thickness, do not add thinner for dilution in principle.
- 4) Pot life at 20°C is 1 hour. At high temperatures such as in summer, only the amount needed for each application should be mixed.
- 5) Make sure to keep the designed film thickness (Standard thickness : 2 mm) by using a brush, a spatula, etc.
- 6) Store the paints in paint store.
- 7) This code is an internal product code of NPMEU. It is not a specific color code.