



antifouling paint for power
boats antifouling
paint for power boats

高速艇・パワーボート用船底防汚塗料

MASSIVE

NEO

安心の高品質を

paint for power boats antifouling paint for power boats
antifouling paint for po
boats
antifouling paint for power
boats antifouling paint for power boats
antifouling paint for power boats antifouling paint for
power boats antifouling
paint for power boats antifouling paint
for power boats
antifouling paint for power
boats antifouling paint for
power boats antifouling paint for power boats



FRP艇・アルミ艇に塗装可



4kg



日本ペイントマリン株式会社

MASSIVE

NEO

マッシュグネオ

特性

塗料種 高硬度型船底防汚塗料

色相 白・黒・グレー

サイズ 4kg

塗装方法 刷毛、ローラー

塗装回数 50 μ m \times 2回塗り

乾燥時間	温度	指触	塗り重ね時間		没水迄の時間	
			最短	最長	最短	最長
	5 $^{\circ}$ C	1時間	16時間	なし	24時間	3ヶ月
	20 $^{\circ}$ C	40分	6 "	"	8 "	2 "
	30 $^{\circ}$ C	30分	4 "	"	6 "	1 "

用途 FRP船 アルミ/軽合金船

適用プライマー MARIART P100, MARIART P200

適用シンナー MARIART AF シンナー



使用量目安

船底防汚塗料使用量目安 (モーターボート※)
(標準塗布量: 50 μ m \times 2回刷毛塗り)

17フィート	4kg
21フィート	6kg
23フィート	8kg
25フィート	9kg
30フィート	12kg

※セーラーボートの使用量目安については塗り方ガイドをご覧ください。

法・通達等にもとづく表示: 危険物表示: 第2石油類(非水溶性)・合成樹脂エナメル塗料
有機溶剤区分: 第2種等

MASSIVE マッシュグネオ 塗装仕様



1 POINT アドバイス



新しい刷毛は使う前にしごき、抜けかかった毛を取り除いてください。




塗料をよく攪拌してから使ってください。



雨天・高湿度の場合、塗装は避けてください。



塗料を希釈する場合は専用シンナーを使ってください。



流水圧のよくかかる場所(船首、船尾、吃水部等)は少し厚めに塗装してください。



概算式で計算された船底塗料使用量を必ず塗りきってください。



塗装間隔及び没水までの時間を守ってください。



残った塗料を保存する場合は専用シンナーを塗料の表面にはり、フタを完全に閉じて保存してください。