

Marine Paint Manual

Reference No. : 17 - 11

Issue Date: August 2019 (ES)

NEOGUARD TOUGHNESS

A high build, high solids and heavy-duty epoxy anticorrosive paint coating suitable for hatch coamings and cargo holds of bulk carriers. Since it has excellent resistance to impact, abrasion, chemicals, water and sea water, the coating provides long term corrosion protection for cargo spaces.

Suitable Use	Cargo holds (wet, dry)				
Type	Epoxy (High solids / High build / High hardness / Two-pack)				
Color	Gray, Red oxide				
Gloss	Flat				
Volume Solids	80 ± 2% (ISO3233:1998)				
Typical Dry Film Thickness	100 ~ 250 μm				
Approx. Wet Film Thickness	125 ~ 313 μm				
Theoretical Coverage	5.33 m²/ L (150 μm)				
Drying Time	Surface Dry	2 hours (5°C)	1 hour (20°C)	40 minutes (30°C)	
	Dry Hard	20 hours (5°C)	7 hours (20°C)	5 hours (30°C)	
	Full cure	10 days (5°C)	6 days (20°C)	5 days (30°C)	
Interval before Overcoating (by self)	Min.	20 hours (5°C)	7 hours (20°C)	5 hours (30°C)	
	Max.	14 days (5°C)	7 days (20°C)	5 days (30°C)	
Thinner	NIPPON MARINE THINNER 600 (0 ~ 10%, by volume)				
Application Method	Airless Spray	Tip range	0.48 ~ 0.59mm		
		Fan angle	55 ~ 62°		
		(For T/U)	30°		
		Output pressure	150~200 kg / cm²		
Mixing Ratio by Volume	Brush / Roller	For touching up small areas only			
	BASE 72 / HARDENER 28				
	Pot Life after Mixing	5 hours (5°C)	3 hours (20°C)	1½ hours (30°C)	
Packaging	Two Packs				
Japan Local Brand	NEOGUARD TOUGHNESS				
Flash Point	BASE 30 °C, HARDENER 30 °C				
Surface Preparation	All surfaces to be coated should be clean, dry and free from contamination.				
	High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.				
	Blast cleaned to ISO-Sa 2 ½ or Power tool cleaned to ISO-St 3 is recommended.				
	Please consult with Nippon Paint Marine representatives for water jetting.				

Marine Paint Manual

NEOGUARD TOUGHNESS

Issue Date: August 2019 (ES)

Safety

Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)
Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapour concentrations within safe limits.
Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

<Note>

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) For availability of product consult Nippon Paint Marine representatives.
- 3) Unit size and filled volumes can vary due to local regulations.
- 4) Store the paints in paint store.