

## Marine Paint Manual

Reference No. 11 - 03

Issue Date: November 2022 (ES)

### AQUATERRAS 6000

A unique and innovative biocide free self-polishing coating based on patented hydrolysis coating technology. Reduction of frictional resistance and prevention shipfouling organism from settling is realized by its hydrophilic & hydrophobic microdomain structures and its hydrolysis reaction. AQUATERRAS differs from the other antifouling paints in no biocide formulation taking the marine environmental issues into consideration. And it provides long-term fouling protection and excellent fuel-saving effect with its stable polishing property. It is designed especially for coastal ships.

Suitable Use	For coastal ships				
Type	Micro-Domain SPC (Biocide free / extra super low friction / Hydrolysis / Advanced fuel-saving / Lower CO <sub>2</sub> emission)				
Colour	Brown, Light Brown, Blue, Black				
Gloss	Semi-gloss				
Volume Solids	37 ± 2% (ISO3233:1998)				
Typical Dry Film Thickness	70 ~ 140 μm				
Approx. Wet Film Thickness	189 ~ 378 μm				
Theoretical Coverage	3.70 m <sup>2</sup> /L (100 μm)				
Drying Time	Surface Dry	1 hour (5°C)	40 minutes (20°C)	30 minutes (30°C)	
	Dry Hard	3 hours (5°C)	1 hour (20°C)	40 minutes (30°C)	
Interval before Overcoating (by self)	Min.	6 hours (5°C)	4 hours (20°C)	3 hours (30°C)	
	Max.	— (5°C)	— (20°C)	— (30°C)	
Interval before Immersion (100 μm)	Min.	18 hours (5°C)	12 hours (20°C)	10 hours (30°C)	
	※ See Note (4).				
Thinner	NIPPON MARINE THINNER 650 (0 ~ 2%, by volume)				
Application Method	Airless Spray	Tip range	0.64 ~ 0.74 mm		
		Fan angle	45° ~ 54°		
		Output pressure	above 150 kg/cm <sup>2</sup>		
	Brush / Roller	For touching up small areas only			
Packaging	Single Pack				
Japan Local Brand	AQUATERRAS 6000				
Flash Point	24°C				
Surface Preparation	All surfaces to be coated should be clean, dry and free from contamination. High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.				

---

## ***Marine Paint Manual***

AQUATERRAS 6000

Issue Date: November 2022 (ES)

### **Safety**

Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)

Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.

Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

### **<Note>**

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Use NIPPON MARINE THINNER 650 to wash painting appliances, hoses and guns before and after use.
- 3) The declaration letter of Tin-free Antifouling Paint would not be issued if mixed with the other antifouling paints product or another chemical products.
- 4) Interval before immersion is related to ambient conditions, ventilation, film thickness, and number of coats and will be affected correspondingly. Contact us for actual application.
- 5) For availability of product consult Nippon Paint Marine representatives.
- 6) Unit size and filled volumes can vary due to local regulations.
- 7) Store the paints in paint store.