

## Marine Paint Manual

Reference No. 11 - 04

Issue Date: November 2022 (ES)

### AQUATERRAS 8000

A unique and innovative biocide free self-polishing coating based on patented hydrolysis coating technology. Reduction of frictional resistance and prevention shipfouling organism from settling is realized by its hydrophilic & hydrophobic microdomain structures and its hydrolysis reaction. AQUATERRAS differs from the other antifouling paints in no biocide formulation taking the marine environmental issues into consideration. And it provides long-term fouling protection and excellent fuel-saving effect with its stable polishing property. It is designed as antifouling coating during outfitting especially for newbuildings.

|                                       |  |                                  |                              |            |        |                   |
|---------------------------------------|--|----------------------------------|------------------------------|------------|--------|-------------------|
| Suitable Use                          | For newbuildings during outfitting etc.  |                                  |                              |            |        |                   |
| Type                                  | Micro-Domain SPC<br>(Biocide free / extra super low friction / Hydrolysis / Advanced fuel-saving / Lower CO <sub>2</sub> emission) |                                  |                              |            |        |                   |
| Colour                                | Brown, Light Brown, Black  |                                  |                              |            |        |                   |
| Gloss                                 | Semi-gloss   |                                  |                              |            |        |                   |
| Volume Solids                         | 37 ± 2% (ISO3233:1998)   |                                  |                              |            |        |                   |
| Typical Dry Film Thickness            | 70 ~ 140 μm  |                                  |                              |            |        |                   |
| Approx. Wet Film Thickness            | 189 ~ 378 μm   |                                  |                              |            |        |                   |
| Theoretical Coverage                  | 3.70 m <sup>2</sup> /L (100 μm)  |                                  |                              |            |        |                   |
| Drying Time                           | Surface Dry  | 1 hour                           | (5°C)                        | 40 minutes | (20°C) | 30 minutes (30°C) |
|                                       | Dry Hard   | 3 hours                          | (5°C)                        | 1 hour     | (20°C) | 40 minutes (30°C) |
| Interval before Overcoating (by self) | Min.   | 6 hours                          | (5°C)                        | 4 hours    | (20°C) | 3 hours (30°C)    |
|                                       | Max.   | —                                | (5°C)                        | —          | (20°C) | — (30°C)          |
| Interval before Immersion (100 μm)    | Min.   | 18 hours                         | (5°C)                        | 12 hours   | (20°C) | 10 hours (30°C)   |
|                                       | ※ See Note (4).  |                                  |                              |            |        |                   |
| Thinner                               | NIPPON MARINE THINNER 650 (0 ~ 2%, by volume)  |                                  |                              |            |        |                   |
| Application Method                    | Airless Spray  | Tip range                        | 0.64 ~ 0.74 mm               |            |        |                   |
|                                       |  | Fan angle                        | 45° ~ 54°                    |            |        |                   |
|                                       |  | Output pressure                  | above 150 kg/cm <sup>2</sup> |            |        |                   |
|                                       | Brush / Roller   | For touching up small areas only |                              |            |        |                   |
| Packaging                             | Single Pack  |                                  |                              |            |        |                   |
| Japan Local Brand                     | AQUATERRAS 8000  |                                  |                              |            |        |                   |
| Flash Point                           | 24°C   |                                  |                              |            |        |                   |
| Surface Preparation                   | All surfaces to be coated should be clean, dry and free from contamination.  |                                  |                              |            |        |                   |
|                                       | High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.                        |                                  |                              |            |        |                   |

---

## ***Marine Paint Manual***

AQUATERRAS 8000

Issue Date: November 2022 (ES)

### **Safety**

Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.)

Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapor concentrations within safe limits.

Prior to use, obtain, consult and follow the SDS for this product concerning health and safety information.

### **<Note>**

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Use NIPPON MARINE THINNER 650 to wash painting appliances, hoses and guns before and after use.
- 3) The declaration letter of Tin-free Antifouling Paint would not be issued if mixed with the other antifouling paints product or another chemical products.
- 4) Interval before immersion is related to ambient conditions, ventilation, film thickness, and number of coats and will be affected correspondingly. Contact us for actual application.
- 5) For availability of product consult Nippon Paint Marine representatives.
- 6) Unit size and filled volumes can vary due to local regulations.
- 7) Store the paints in paint store.